

In the Claims:

1-56. (cancelled)

57. =(Currently amended) A combination of ingredients forming a retroreflective ink, the combination comprising retroreflective elements, microbeads additional to said retroreflective elements and/or constituting said retroreflective elements at least in part, binder chemicals for attaching the retroreflective elements and microbeads to a substrate to which the ink is to be applied, and a coupling agent for coupling the microbeads and cross-linking the binder chemicals, the coupling agent being unreactive and uncured until a curing step is carried out and reactive when the curing step is carried out during which ~~the~~ a temperature of the substrate and ink applied to the substrate is elevated to between 60 and 200°C, the coupling agent having a storage life of not less than about 3 months and being unreactive except at elevated temperature of the curing step, the coupling agent being selected from the group consisting of an aminoalkyl silanetriol and a blocked polyisocyanate.

58. (cancelled)

59. (Previously presented) The combination of claim 57 wherein at least some of the microbeads are without the retroreflective elements.

60. (Previously presented) The combination of claim 57 wherein the binder chemical and the coupling agent are selected from the group consisting of:

a polyvinylidene chloride copolymer is the binder chemical and (3-aminopropyl) silanetriol and/or blocked 1,6 hexamethylene diisocyanate trimer is the coupling agent,

an acrylic copolymer is the binder chemical and (3-aminopropyl) silanetriol and/or blocked 1,6 hexamethylene diisocyanate trimer is the coupling agent, and

a polyurethane is the binder chemical and blocked 1,6 hexamethylene diisocyanate trimer is the coupling agent.

61. (Previously presented) The combination of claim 57 further comprising one or more components selected from the group consisting of:

pigment, humectant, urea, urea and 2,3 propane diol, buffer, ammonium or sodium phosphates buffer, dispersant, defoamer, thickening agent, cross-linking agent, softening agent, carbon black, UV absorbing material, anti-scuffing agent, a silicone or fluoropolymer, light spill-suppressing agent, anti-static agent, water repellant agent, a silicone, and a fluoropolymer.

62. (Previously presented) The combination of claim 57 wherein the volume ratio of the binder to the microbeads is equal to or less than 50%.

63. (Previously presented) The combination of claim 57 wherein essentially all of the microbeads are unmetallised and the retroreflective elements include reflective flake particles.

64. (Previously presented) The combination of claim 57 wherein the binder forms at least part of a liquid carrier medium for the retroreflective elements or microbeads.

65. (Previously presented) The combination of claim 57 wherein the binder chemicals, retroreflective elements and microbeads are comprised of a one-pack retroreflective ink or a two-pack retroreflective ink having the coupling agent as the second pack.

66. (Previously presented) The combination of claim 65 wherein the two-pack ink includes a reactive polyisocyanate or an alkoxysilyl alkyl derivative.

67. (Previously presented) The combination of claim 57 wherein the microbeads are metallised with an aluminium coating that is superposed on stannous chloride.

68. (Previously presented) The combination of claim 67 wherein the microbeads are treated with a compound selected from the group consisting of a silicate, a sodium silicate, a silane, an amino silane, and a bis-*[gamma]*-(trimethoxysilyl) propyl] amine.

69. (Previously presented) The combination of claim 67 wherein the metallised microbeads are coated with a silicate or silane that is superposed on the metallised microbeads.

70. (Previously presented) A composition that is a one-pack or a two-pack retroreflective ink which is comprised of the combination claimed in claim 57.

71. (Previously presented) The combination of claim 70 wherein the retroreflective ink is water-based.

72. (Previously presented) The combination of claim 71 that is suitably formulated for screen printing.

73. (Previously presented) The combination of claim 70 wherein the ink has a viscosity that is less than or equal to about 40 Pascal seconds at room temperature.

74. (Withdrawn) A composition that is microbeads for use in the production of a retroreflective ink, the microbeads having applied thereto one or more of the group comprising silicate, a silane, an amino silane, bis-*[gamma]*-(trimethoxysilyl) propyl] amine and stannous chloride.

75. (Withdrawn) The composition of claim 74 wherein the microbeads are metallised with a coating of aluminium superposed on the stannous chloride.

76. (Withdrawn) The composition of claim 75 wherein the silicate is superposed on the metallised aluminium coated beads and the silane is superposed on the silicate.

7877. (Withdrawn-currently amended) The composition of claim 74 wherein the microbeads have one or more of the following characteristics selected from the group consisting of: a refractive index in the range of about 1.8 to 2.2, a median size of the microbeads in the range of about 10 to 100 microns and the microbeads are composed of titanium glass or barium glass.

79.78. (Withdrawn-currently amended) A composition that is a retroreflective ink which contains microbeads as claimed in claim 74.

80.79. (Withdrawn-currently amended) The composition of claim 7877 which includes binder chemicals for attaching the microbeads to a substrate to which the ink is to be applied.

81.80. (Withdrawn-currently amended) The composition of claim 8079 which includes a coupling agent ~~for coupling~~ for coupling the microbeads and for cross-linking the binder chemicals, the coupling agent being unreactive until the printing process is carried out.

82.81. (Currently amended) A method for making a one-pack retroreflective ink comprising the steps of:

- (a) making microbeads;
- (b) suspending the microbeads in a liquid carrier medium, the liquid carrier medium is comprised of binder chemicals for attaching the microbeads to a substrate to which the ink is to be applied and a coupling agent which couples the microbeads and cross-links the binder chemicals, the one-pack retroreflective ink having a storage life of not less than about 3 months and the coupling agent being unreactive and uncured until a curing step is carried out and reactive when the curing step is carried out during which ~~the~~ a temperature of the substrate and ink applied to the substrate is elevated to between 60 and 200°C, the coupling agent having a storage life of not less than about 3 months and being unreactive except at elevated temperature of the curing step, the coupling agent being selected from the

group consisting of an aminoalkyl silanetriol and a blocked polyisocyanate.

| ~~83.82.~~ (Currently amended) The method of claim ~~8281~~ wherein step (a) includes applying an aluminium coating to the microbeads.

| ~~84.83.~~ (Currently amended) The method of claim ~~8382~~ wherein step (a) includes pre-treating the microbeads with stannous chloride prior to application of the aluminium coating.

| ~~85.84~~ (Currently amended) The method of claim ~~8483~~ wherein step (a) includes treating the microbeads with a dilute aqueous solution of stannous chloride.

| ~~8685.~~ (Currently amended) The method of claim ~~8281~~ wherein step (a) includes hemispherically metallising the microbeads in a vacuum metallising process in which the microbeads are held on a film with an adhesive coating for transport through the metallising process, the adhesive coating is comprised of styrene-butadiene type adhesive.

| ~~8786.~~ (Currently amended) The method according to claim ~~8685~~ wherein step (a) includes passing the film through an aqueous solution of citric acid after metallisation.

| ~~8887.~~ (Currently amended) The method of claim ~~8685~~ wherein step (a) includes ultrasonically treating the film to assist in release of the microbeads from the adhesive.

| ~~89.88.~~ (Currently amended) The method of claim ~~8584~~ wherein step (a) includes treating the microbeads prior to inclusion in the ink with a silicate.

| ~~90.89.~~ (Currently amended) The method of claim ~~8281~~ wherein step (a) includes treating the microbeads with a silane or an amino silane prior to inclusion in the ink.

| 91.90. (Currently amended) The method of claim 8988 wherein step (a) includes treating the microbeads with a compound selected from the group consisting of a silane, an amino silane and bis-[*gamma*-(trimethoxysilyl) propyl] amine after the silicate treatment.

| 92.91. (Currently amended) The method of claim 8281 wherein step (a) includes adding an amino silanetriol or a blocked polyisocyanate to the liquid carrier medium as coupling agent.

| 93.92. (Currently amended) The method of claim 8281 wherein step (a) includes preparing the liquid carrier medium from the binder chemicals and the coupling agent before suspending the microbeads in the liquid carrier medium.

| 94.93. (Currently amended) The method of claim 9392 wherein the liquid carrier medium of step (b) includes additives selected from the group consisting of:

pigment, humectant, urea, urea and 2,3 propane diol, buffer, ammonium or sodium phosphate buffer, dispersant, defoamer, thickening agent, cross-linking agent, softening agent, carbon black, UV absorbing material, anti-scuffing agent, silicone, fluoropolymer, light spill-suppressing agent, anti-static agent and water repellant agent.

| 95.94. (Currently amended) The method of claim 9493 wherein step (b) includes adding a thickener to the liquid carrier medium before or after the addition of the binder chemicals and coupling agent.

| 96.95. (Currently amended) A composition of an ink produced by the method of claim-8281.

| 97.96. (Currently amended) A composition of a substrate coated or printed with a composition of claim-9695.

| 98.97. (Currently amended) The composition of claim 9796 wherein the substrate is a screen for displaying projected images or a studio background for chroma-keying applications.

~~99~~98. (Currently amended) The composition of claim ~~97~~96 wherein the substrate is a flexible tape.

~~100~~99. (Currently amended) The method of providing a substrate having a retroreflective coating, comprising the steps of:

applying to the substrate an ink as claimed in claim ~~96~~95 wherein the ink is formulated as a one-pack retroreflective ink and the coupling agent is activated after the ink is printed or coated on to the substrate.

~~101~~100. (Currently amended) The method of claim ~~100~~99 wherein the coupling agent is activated by curing the ink coating at elevated temperature.

~~102~~101. (Currently amended) The method of claim ~~100~~99 wherein the coupling agent is activated by UV light or other high energy radiation during or after the printing process.

~~103~~102. (Currently amended) The composition of claim ~~96~~95 wherein the ink is a retroreflective one-pack ink having a storage life of not less than about 3 months.

~~104~~103. (Currently amended) The composition of claim ~~103~~102 wherein the retroreflective one-pack ink has a viscosity of between about 10 and 30 Pascal seconds after storage of not less than about 3 months.

~~105~~104. (Currently amended) The composition of claim ~~103~~102 wherein the retroreflective one-pack ink applied to the substrate and cured has a laundering durability such that the retroreflectivity is not reduced by more than about 40% when the substrate is in the form of a cotton, nylon or polyester fabric and laundered for 5 cycles in accordance with ISO 6330, method 5A.

~~106.105.~~ (Withdrawn-currently amended) A composition of a fabric having fireproof or fire retardant properties that is printed or coated with a retroreflective ink which is comprised of retroreflective elements in a polymeric matrix, the fabric comprising a structural component that chars before it melts.

~~107.106.~~ (Withdrawn-currently amended) The composition of claim ~~106.105~~ wherein the fabric is made fireproof or fire retardant by application of a fire retardant agent.

~~108.107.~~ (Withdrawn-currently amended) The composition of claim ~~107.106~~ wherein the fire retardant agent is applied to a cellulosic, the fire retardant agent is selected from the group consisting of Proban ® RTM and Pyrovatex ® RTM.

~~109.108.~~ (Withdrawn-currently amended) The composition of claim ~~106.105~~ wherein the fabric is comprised of an aramid fiber.

~~110.109.~~ (Withdrawn-currently amended) The composition of claim ~~106.105~~ wherein the fabric is non-burning after a retroreflective ink has been applied to the fabric.

~~111.110.~~ (Withdrawn-currently amended) The composition of claim ~~110.109~~ wherein the ink is aqueous-based and the polymeric matrix comprises polyvinylidene chloride.

~~112.111.~~ (Withdrawn-currently amended) The composition of claim ~~110.111~~ wherein the polymeric matrix comprises polyvinyl chloride or other non-flammable plastisol.

~~113.112.~~ (Withdrawn-currently amended) A composition that is a fireproof or fire retardant fabric printed or coated with a retroreflective ink which is comprised of retroreflective elements in a polymeric matrix, the fabric is comprised of a structural component that chars before it melts, the ink is comprised of an ink as claimed in claim 70.

~~114.113.~~ (Currently amended) The composition of claim 57, wherein the coupling agent has a storage life of not less than about 3 months and is unreactive except at elevated temperature of between 130 and 180°C at which the one-pack retroreflective ink printed on the substrate is cured.

~~115.114.~~ (Currently amended) The method of claim ~~82~~81, wherein the coupling agent has a storage life of not less than about 3 months and is unreactive except at elevated temperature of between 130 and 180°C at which the one-pack retroreflective ink printed on the substrate is cured.

~~116.115.~~ (Currently amended) The combination of claim 68 wherein the microbeads have at least one of the following characteristics selected from the group consisting of: a refractive index in the range of about 1.8 to 2.2, a median size of the microbeads in the range of about 10 to 100 microns and the microbeads are composed of titanium glass or barium glass.

~~117.116.~~ (Currently amended) The method of claim ~~91~~90 wherein the microbeads have at least one of the following characteristics selected from the group consisting of: a refractive index in the range of about 1.8 to 2.2, a median size of the microbeads in the range of about 10 to 100 microns and the microbeads are composed of titanium glass or barium glass.

117. (New) A combination of ingredients forming a retroreflective ink, the combination comprising retroreflective elements, microbeads additional to said retroreflective elements and/or constituting said retroreflective elements at least in part, binder chemicals for attaching the retroreflective elements and microbeads to a substrate to which the ink is to be applied, and a coupling agent for coupling the microbeads and cross-linking the binder chemicals, the coupling agent being unreactive and uncured until a curing step is carried out and reactive when the curing step is carried out during which a temperature of the substrate and ink applied to the substrate is elevated to between 60 and 200°C, the coupling agent having a storage life of not less than about 3 months and being unreactive except at elevated temperature of the curing step, the coupling

agent being selected from a group consisting of an aminoalkyl silanetriol and a combination of aminoalkyl silanetriol and blocked polyisocyanate.

118. (New) A method for making a one-pack retroreflective ink comprising the steps of:

- (a) making microbeads;
- (b) suspending the microbeads in a liquid carrier medium, the liquid carrier medium is comprised of binder chemicals for attaching the microbeads to a substrate to which the ink is to be applied and a coupling agent which couples the microbeads and cross-links the binder chemicals, the one-pack retroreflective ink having a storage life of not less than about 3 months and the coupling agent being unreactive and uncured until a curing step is carried out and reactive when the curing step is carried out during which a temperature of the substrate and ink applied to the substrate is elevated to between 60 and 200°C, the coupling agent having a storage life of not less than about 3 months and being unreactive except at elevated temperature of the curing step, the coupling agent being selected from a group consisting of an aminoalkyl silanetriol and a combination of aminoalkyl silanetriol and blocked polyisocyanate.